

In the Claims

1. (Currently Amended) A dehydrogenation catalyst comprising from about 50 to about 90 percent by weight of eta alumina, from about 10 to about 30 percent by weight of a chromium compound, and from about 0.1 to ~~about 5~~ 1 percent by weight of a zirconium compound, added as a stabilizing material.

2. (Original) The dehydrogenation catalyst of Claim 1 wherein the eta alumina comprises from about 70 to about 90 percent of the catalyst by weight.

3. (Original) The dehydrogenation catalyst of Claim 1 wherein the chromium compound comprises chromium oxide and comprises from about 15 to about 25 percent of the catalyst by weight.

4. (Cancelled)

5. (Original) The dehydrogenation catalyst of Claim 1 wherein the surface area of the catalyst is from about 120 to about 60 m²/g.

6. (Original) The dehydrogenation catalyst of Claim 1 further comprising an alkali metal additive.

7. (Original) The dehydrogenation catalyst of Claim 6 wherein the alkali metal is selected from the group consisting of potassium, sodium and cesium.

8. (Original) The dehydrogenation catalyst of Claim 6 wherein the alkali metal comprises potassium.

9. (Original) The dehydrogenation catalyst of Claim 6 wherein the alkali metal comprises sodium.

10. (Original) The dehydrogenation catalyst of Claim 6 wherein the alkali metal comprises cesium.

11. (Currently Amended) A method for the preparation of a dehydrogenation catalyst comprising

preparing an eta alumina carrier, impregnating the eta alumina carrier with a chromium compound, impregnating the chromium impregnated carrier with a zirconium compound as a stabilizer, calcining the impregnated carrier material to form the dehydrogenation catalyst,

wherein the chromium material comprises from about 10 to about 30 percent of the catalyst by weight and wherein the zirconium material comprises from about 0.1 to ~~about 5~~ 1 percent of the catalyst by weight.

12. (Currently Amended) The method of Claim 11 wherein the catalyst comprises from about 70 to about 90 percent by weight eta alumina, from about 15 to about 25 percent by weight chromia and from about 0.1 to ~~about~~ 1 percent by weight zirconia, as a stabilizing material.

13. (Original) The method of Claim 11 wherein the composition of the catalyst further comprises from about 0.1 to about 5 percent by weight of an alkali metal additive.

14. (Original) The method of Claim 13 wherein the alkali

metal is selected from the group consisting of potassium, sodium and cesium.

15. (Original) The method of Claim 14 wherein the alkali metal comprises potassium.

16. (Original) The method of Claim 14 wherein the alkali metal comprises sodium.

17. (Original) The method of Claim 14 wherein the alkali metal comprises cesium.

18. (Currently Amended) A method for the preparation of a dehydrogenation catalyst comprising

preparing an eta alumina carrier, coimpregnating the eta alumina carrier with a chromium compound and a zirconium compound as a stabilizer, calcining the impregnated carrier material to form the dehydrogenation catalyst,

wherein the chromium material comprises from about 10 to about 30 percent of the catalyst by weight and wherein the zirconium material comprises from about 0.1 to ~~about 5~~ 1 percent of the catalyst by weight.

19. (Currently Amended) The method of Claim 18 wherein the catalyst comprises from about 70 to about 90 percent by weight eta alumina, from about 15 to about 25 percent by weight chromia and from about 0.1 to ~~about~~ 1 percent by weight zirconia, as a stabilizing material.

20. (Original) The method of Claim 18 wherein the composition

of the catalyst further comprises from about 0.1 to about 5 percent by weight of an alkali metal additive.

21. through 23. (Cancelled)

Basis for Amendments

The applicants have amended Claims 1, 11, 12, 18 and 19 to clarify that the amount of zirconium that is present in the dehydrogenation catalyst of the application is from about 0.1 to 1 percent by weight. Basis for this amendment is contained on page 11, lines 6 - 9. No new subject matter is introduced by this Amendment.